

Report No. : CH:TX:1142017942-1

DATE : 08/07/2020



THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS:

SAMPLE DESCRIPTION NON-WOVEN FABRIC
BERMED PP SPUNBOND 20 GSM
COLOUR WHITE
COUNTRY OF ORIGIN POLAND
COUNTRY OF DESTINATION POLAND
SAMPLE RECD ON 16/06/2020 TESTING PERIOD: 16/06/2020 - 04/07/2020

Summary of Test Results

Test Method	Test Name	Status / Performance Level
ISO 9073-17:2008	Water Impact Penetration Test	Refer results
ISO 9073-3:1989	Tensile Strength (Dry & Wet conditions)	Refer results
EN ISO 13938-1: 2019	Bursting Strength (Dry & Wet conditions)	Refer results

per pro SGS India Private Ltd.

G. NAGESWARA RAO
EXECUTIVE

Email your Test Report Related Enquiries at Feedback.SLT@sgs.com

Test report revised to correct the sample image as per customer request.

This Report cancels and supersedes the Report No 1142017942 Dated 04/07/2020 issued by SGS India

JOE No. : 2042809706

Page 1 of 3

Control No.: 1142520132

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm and Terms and Conditions for electronic documents www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company.

Report No. : CH:TX:1142017942-1

DATE : 08/07/2020



RESULTS

WATER IMPACT PENETRATION TEST

ISO 9073-17: 2008

Test Side: Face side

Distilled Water Temperature: 27 ± 1°C

Weight of blotter gained(grams)

1	22.5
2	21.3
3	22.1
4	21.8
5	20.8
Average:	21.7
S.D	0.67

TENSILE STRENGTH

ISO 9073-3: 1989

Type of Machine used: CRE

DRY CONDITION

DIRECTION 1	38.0 N
DIRECTION 2	16.6 N

WET CONDITION

DIRECTION 1	42.2 N
DIRECTION 2	16.8 N

BURSTING STRENGTH

EN ISO 13938-1: 2019

Machine Used: Mullen Type

Diaphragm Used:38mm

DRY CONDITION

67.5 kPa

WET CONDITION

66.2 kPa

Report No. : CH:TX:1142017942-1

DATE : 08/07/2020

SAMPLE IMAGE

***** End of Report*****